



PRODUCT DATA SHEET – PTI ADDITIVES

POLYKICK™ ACCELERATOR

DESCRIPTION

POLYKICK™ is a paint additive formulated by Products Techniques Inc. to accelerate the air dry time of two component polyurethane topcoat systems. While this product reduces dry times it will not accelerate chemical cure rates. A full chemical cure for two component polyurethane systems typically takes 4 to 7 days. **POLYKICK™** will accelerate the dry time of any two component polyurethane system not just PTI's coatings.

COATING PROPERTIES & CHARACTERISTICS

Flash Point	116°F
Weight (lbs per gallon)	7.2 lbs
Color	Clear
Volatile Organic Compounds (VOC)	959 g/l
Specifications	Proprietary

SHELF LIFE

Shelf life is only applicable for materials stored in unopened and undamaged original factory filled containers. 1 year when stored at 50°-85° F.

MIXING INSTRUCTIONS

Shake PolyKick for 1 – 2 minutes for optimal results. Add PolyKick to the Polyurethane Topcoat according to the instructions below.

At 1% by weight added to admixed material:

Tack free: 1 hour
Dry hard: 1.5 hours
Material jelled: 2.5 hours

At 5% by weight added to admixed material:

Tack free: 20 minutes
Dry hard: 30 minutes
Material jelled: 45 minutes

Do not add more than 5%. Addition of more than 5% may adversely affect the quality of the cured topcoat.

HEALTH, SAFETY, & STORAGE REQUIREMENTS

Refer to each individual material SDS (Safety Data Sheet) for specific requirements on the health, safety, storage and handling requirements. Follow all local, state, and national regulations during surface preparation, material application and cleanup.

PRODUCT INFORMATION & DISCLAIMER

Product Data Sheets are periodically updated to reflect new information. It is important to use the latest and most recent revision for the product being used. The foregoing information is accurate to the best of our knowledge. However, due to differences in customer handling, use and method of application which are not known and are beyond our control, Products Techniques, Inc. makes no warranties as to the end result.